

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 : A61K 6/00, 7/00	A1	(11) International Publication Number: WO 00/64401 (43) International Publication Date: 2 November 2000 (02.11.00)
(21) International Application Number: PCT/US00/11359 (22) International Filing Date: 26 April 2000 (26.04.00) (30) Priority Data: 09/298,895 26 April 1999 (26.04.99) US (71) Applicant: REVLON CONSUMER PRODUCTS CORPORATION [US/US]; 625 Madison Avenue, New York, NY 10022 (US). (72) Inventors: JOSE, Natividad; 84-35 Lander Street #5C, Jamaica, NY 11435 (US). URENECK, Ann, Marshall; 36 Rutledge Drive, Redbank, NJ 07701 (US). (74) Agents: INSOGNA, Anthony, M. et al.; Pennic & Edmonds LLP, 1155 Avenue of the Americas, New York, NY 10036 (US).		(81) Designated States: AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: COLOR COSMETIC COMPOSITIONS CONTAINING ORGANIC OIL AND SILICONE MIXTURE (57) Abstract A pigmented cosmetic composition comprising at least one silicone compatible organic oil and at least two silicones selected from the group consisting of: (A) D _a ; (B) MD _b D' _c D'' _d M; (C) M _e T _f ; (D) M _g Q _h ; wherein a is 3-6; b is 1-1,000,000, preferably 1-50,000, more preferably 1-5,000; c is 0-1,000,000, preferably 0-50,000, more preferably 0-5,000; d is 0-1,000,000, preferably 0-50,000, more preferably 0-5,000; e is 1-1,000; f is 1-1,000; g is 1-1,000; and h is 1-1,000.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

COLOR COSMETIC COMPOSITIONS CONTAINING ORGANIC OIL AND SILICONE MIXTURE

Technical Field

5 The invention is in the field of color cosmetic compositions for application to skin and lips.

Background of the Invention

Recently transfer resistant cosmetic compositions have become very popular.

10 Women of the nineties lead busy lives and are interested in color cosmetic products that are long lasting and comfortable to wear. While the current transfer resistant cosmetics stay on the skin very well, in some cases they tend to be drying and uncomfortable to wear. In addition, transfer resistant films also tend to have a matte texture, which some women do not find attractive. The ideal color cosmetic composition should be durable and long
15 lasting, comfortable to wear, and provide a finish which is semi-matte or even shiny.

The object of the invention is to provide a color cosmetic composition that provides a long lasting durable finish on the skin and is comfortable to wear.

Another object of the invention is to provide a color cosmetic composition that is transfer resistant and provides a semi-matte or shiny finish.

20 Another object of the invention is to provide a transfer resistant lipstick composition that provides a semi-matte or shiny finish on the lips.

Summary of the Invention

The invention comprises a pigmented cosmetic composition comprising at least one
25 silicone compatible organic oil and at least two silicones selected from the group consisting of:

(A) D_a

(B) $MD_bD'_cD''_dM$

(C) M_eT_f

30 (D) M_gQ_h

wherein a is 3-6

b is 1-1,000,000, preferably 1-50,000, more preferably 1-5,000

c is 0-1,000,000, preferably 0-50,000, more preferably 0-5,000

d is 0-1,000,000, preferably 0-50,000, more preferably 0-5,000

35 e is 1-1,000

f is 1-1,000

g is 1-1,000; and
h is 1-1,000.

Detailed Description

5 The color cosmetic composition of the invention may be a lipstick in the stick or liquid form, blush, eyeshadow, foundation, concealer, and the like, and may be in the anhydrous or emulsion form. The composition contains at least one silicone compatible organic oil and at least two silicones, preferably three, silicones selected from the group consisting of (A) - (D), above.

10

I. SILICONE COMPATIBLE ORGANIC OIL

The silicone compatible organic oil may be an ester, hydrocarbon oil, or an animal, vegetable, or mineral oil. The term "compatible" means that the organic oil is soluble or dispersible in the silicone mixture to form a stable solution or dispersion. The organic oil is
15 a liquid at room temperature (25° C.) and preferably has a viscosity of about 10 to 600,000, preferably 20 to 500,000, more preferably 50 to 300,000 centipoise at 25° C. The composition comprises 0.1-80%, preferably 0.5-70%, more preferably 1-50% by weight of the total composition of the silicone compatible organic oil.

20

A. Esters

Suitable silicone compatible organic esters are mono-, di-, and triesters. The composition may comprise one or more esters selected from the group, or mixtures thereof. Preferably the composition contains a mixture of di- and triesters, and in a ratio of 0.1-10% diester and 0.1-15% triester, by weight of the total composition. Particularly preferred
25 compositions comprise a mixture of mono-, di- and triesters in a ratio of 0.01-10% monoester, 0.1-10% diester, and 0.1-15% triester, all percentages being by weight of the total composition.

1. Monoesters

30 Monoesters are defined as esters formed by the reaction of a monocarboxylic acid having the formula R-COOH, wherein R is a straight or branched chain saturated or unsaturated alkyl having 2 to 30 carbon atoms, or phenyl; and an alcohol having the formula R-OH wherein R is a straight or branched chain saturated or unsaturated alkyl having 2-30 carbon atoms, or phenyl. Both the alcohol and the acid may be substituted with
35 one or more hydroxyl groups, and in one preferred embodiment of the invention the acid is an alpha hydroxy acid. Either one or both of the acid or alcohol may be a "fatty" acid or

alcohol, *i.e.* may have from about 6 to 22 carbon atoms. Examples of monoester oils that may be used in the compositions of the invention include hexyldecyl benzoate, hexyl laurate, hexadecyl isostearate, hexydecyl laurate, hexyldecyl octanoate, hexyldecyl oleate, hexyldecyl palmitate, hexyldecyl stearate, hexyldodecyl salicylate, hexyl isostearate, butyl acetate, butyl isostearate, butyl oleate, butyl octyl oleate, cetyl palmitate, cetyl octanoate, cetyl laurate, cetyl lactate, cetyl isononanoate, cetyl stearate, stearyl lactate, stearyl octanoate, stearyl heptanoate, stearyl stearate, and so on. It is understood that in the above nomenclature, the first term indicates the alcohol and the second term indicates the acid in the reaction, *i.e.* stearyl octanoate is the reaction product of stearyl alcohol and octanoic acid. Preferred is monoester which is the reaction product of an aliphatic C_{2-8} alcohol and a C_{14-22} fatty acid, more particularly, the reaction product of a hexyl alcohol and lauric acid, also referred to as hexyl laurate.

2. Diesters

Suitable diesters that may be used in the compositions of the invention are the reaction product of a dicarboxylic acid and an aliphatic or aromatic alcohol. The dicarboxylic acid may contain from 2 to 30 carbon atoms, and may be in the straight or branched chain, saturated or unsaturated form. The dicarboxylic acid may be substituted with one or more hydroxyl group. The aliphatic or aromatic alcohol may also contain 2 to 30 carbon atoms, and may be in the straight or branched chain, saturated, or unsaturated form. The aliphatic or aromatic alcohol may be substituted with one or more substituents such as hydroxyl. Preferably, one or more of the acid or alcohol is a fatty acid or alcohol, *i.e.* contains 14-22 carbon atoms. The dicarboxylic acid may also be an alpha hydroxy acid. Examples of diester oils that may be used in the compositions of the invention include diisostearyl malate (the reaction product of isostearic alcohol and malic acid), neopentyl glycol dioctanoate (the reaction product of neopentyl glycol and 2-ethyl hexanoic acid), dibutyl sebacate (reaction product of butyl alcohol and sebacic acid), di- C_{12-13} alkyl malate (reaction product of C_{12-13} alcohol and malic acid), dicetearyl dimer dilinoleate (reaction product of cetearyl alcohol and adipic acid), dicetyl adipate (reaction product of cetyl alcohol and adipic acid), diisocetyl adipate (reaction product of hexadecyl alcohol and adipic acid), diisononyl adipate (reaction product of isononyl alcohol and adipic acid), diisostearyl dimer dilinoleate (reaction product of isostearyl alcohol and dilinoleic acid), disostearyl fumarate (reaction product of isostearyl alcohol and fumaric acid), and so on.

3. Triesters

Suitable triesters comprise the reaction product of a tricarboxylic acid and an aliphatic or aromatic alcohol. As with the mono- and diesters mentioned above, the acid and alcohol contain 2 to 30 carbon atoms, and may be saturated or unsaturated, straight or branched chain, and may be substituted with one or more hydroxyl groups. Preferably, one or more of the acid or alcohol is a fatty acid or alcohol containing 14 to 22 carbon atoms. Examples of triesters include triarachidin (reaction product of glycerin and arachidic acid), tributyl citrate (reaction product of butyl alcohol and citric acid), tri C12-13 alkyl citrate (reaction product of C12-13 alcohol and citric acid), tricaprylin (reaction product of glycerin and caprylic acid), tricaprylyl citrate (reaction product of capryl alcohol and citric acid), tridecyl behenate (reaction product of tridecyl alcohol and behenic acid), trioctyldodecyl citrate (reaction product of octyldodecyl alcohol and citric acid), tridecyl behenate (reaction product of tridecyl alcohol and behenic acid), tridecyl cocoate (reaction product of tridecyl alcohol and coconut acid), tridecyl isononanoate (reaction product of tridecyl alcohol and isononanoate), and so on. Preferred is a triester which is the reaction product of an alpha hydroxy acid and a guerbet alcohol having 6 to 30 carbon atoms, in particular the reaction product of citric acid and octyldodecyl alcohol, referred to as trioctyldodecyl citrate.

B. Hydrocarbon Oils.

Suitable hydrocarbon oils used in the compositions of the invention may be volatile or nonvolatile. The term "volatile" means that the oil has a measureable vapor pressure, or a vapor pressure of at least 2 mm. of mercury at 20° C. The term "nonvolatile" means that the oil has a vapor pressure of less than 2 mm. of mercury at 20° C.

1. Volatile Hydrocarbon Oils

Examples of volatile hydrocarbon oils that may be used in the compositions of the invention include various straight or branched chain paraffinic hydrocarbons having 5 to 20 carbon atoms, more preferably 8-20 carbon atoms. Suitable hydrocarbons include pentane, hexane, heptane, decane, dodecane, tetradecane, tridecane, and C₈₋₂₀ isoparaffins as disclosed in U.S. patent nos. 3,439,088 and 3,818,105, both of which are hereby incorporated by reference. Preferred volatile paraffinic hydrocarbons have a molecular weight of 70-225, preferably 160 to 190 and a boiling point range of 30 to 320, preferably 60-260 degrees C., and a viscosity of less than 10 cs. at 25 degrees C. Such paraffinic hydrocarbons are available from EXXON under the ISOPARS trademark, and from the Permethyl Corporation. Suitable C₁₂ isoparaffins are manufactured by Permethyl Corporation under the tradename Permethyl 99A. Another C₁₂ isoparaffin (isododecane) is distributed by Presperse under the tradename Permethyl 99A. Various C₁₆ isoparaffins

commercially available, such as isohexadecane (having the tradename Permethyl R), are also suitable.

2. Nonvolatile Hydrocarbon Oils

Suitable nonvolatile hydrocarbon oils include isoparaffins and olefins having greater than 20 carbon atoms. Examples of such hydrocarbon oils include C_{24-28} olefins, C_{30-45} olefins, C_{20-40} isoparaffins, hydrogenated polyisobutene, mineral oil, pentahydrosqualene, squalene, squalane, and mixtures thereof.

C. Lanolin Oil

Also suitable for use in the composition is lanolin oil or derivatives thereof such as hydroxylated lanolin, isobutylated lanolin oil, acetylated lanolin, acetylated lanolin alcohol, and so on.

Preferred compositions of the invention comprise a silicone compatible organic oil selected from the group consisting of:

- (i) monoesters,
- (ii) diesters,
- (iii) triesters
- (iv) volatile hydrocarbons,
- (v) lanolin; and
- (vi) mixtures thereof.

II. SILICONE MIXTURE

The composition of the invention comprises at least two silicones selected from the group consisting of:

- (A) Da
- (B) $MD_bD'_cD''_dM$
- (C) M_eT_f
- (D) M_gQ_h


wherein a is 3-6

- b is 1-1,000,000, preferably 1-50,000, more preferably 1-5,000
- c is 0-1,000,000, preferably 1-50,000, more preferably 1-5,000
- d is 0-1,000,000, preferably 1-50,000, more preferably 1-5,000
- e is 1-1,000
- f is 1-1,000
- g is 1-1,000; and
- h is 1-1,0000.

The term "M" means a monofunctional monomer unit, "D" means a difunctional monomer unit, "T" means a trifunctional monomer unit, and "Q" a quadrfunctional monomer unit. Primes, *e.g.* D', are used to indicate substituents other than methyl. The silicone mixture comprises 1-75%, preferably 10-70%, more preferably 15-60% by weight of the total composition of the total composition.

A. D_n Silicone

The silicone mixture may comprise one or more silicones having the general formula D_n , wherein D is a difunctional cyclic monomer, in particular dimethylsiloxo, and a



is 3-6. Preferably, the composition comprises 1-40%, more preferably 3-35%, most preferably 5-30% by weight of the total composition of the D_n silicone. D_n silicones are cyclic silicones wherein n is 4 to 6, having the general formula:

wherein $n = 3-6$.

Such cyclic volatile silicones are available from various commercial sources including Dow Corning Corporation and General Electric. The Dow Corning volatile silicones are sold under the tradenames Dow Corning 244, 245, 344, and 200 fluids. These fluids comprise octamethylcyclotetrasiloxane, decamethylcyclopentasiloxane, and mixtures thereof.

B. The $MD_bD'_cD''_dM$ silicone

The silicone mixture used in the compositions of the invention may comprise one or more silicones having the general formula $MD_bD'_cD''_dM$, wherein M is a monofunctional monomer, D is a difunctional monomer, and D' and D'' are difunctional monomers having substituents other than methyl, and wherein b, c, and d are as defined above. The composition may comprise 0.5-45%, preferably 1-40%, more preferably 2-35% by weight of the total composition of one or more $MD_bD'_cD''_dM$ silicones. Preferably this silicone is a

mixture comprising at least one silicone which is a liquid at room temperature and at least one silicone which is a solid or semi-solid at room temperature (*e.g.* 25° C.)

In the above formula, M has the empirical formula $R_3SiO_{0.5}$, or $R^1RRSiO_{0.5}$, or $R^1R^2RSiO_{0.5}$, or $R^1R^2R^3SiO_{0.5}$, wherein R is methyl, and R^1 , R^2 , and R^3 are each independently a C_{1-6} straight or branched chain alkyl, phenyl, diisostearoyl trimethylol propane, or dilauroyltrimethylolpropane. Preferably M has the empirical formula $R_3SiO_{0.5}$, wherein R is methyl.

D has the empirical formula $R_2SiO_{1.0}$ wherein R is methyl.

D' has the empirical formula $RR^4SiO_{1.0}$ or $R^4R^5SiO_{1.0}$ wherein R is methyl and R^4 and R^5 are each independently a C_{7-30} straight or branched chain alkyl, alkenyl, hydroxy-substituted alkyl, fluoro-substituted alkyl, phenyl, trimethylsiloxy, and the like.

D'' has the empirical formula $RR^6SiO_{1.0}$ or $R^6R^7SiO_{1.0}$ wherein R is methyl and R^6 and R^7 are each independently a hydrophilic radical such as $(CH_2)_o-O-PE$ where PE is $(-C_2H_4O)_x(-C_3H_6O)_yH$, and $o = 0-40$; wherein x is 1-10,000 and y is 0-10,000; wherein x is 1-10,000 and y is 0-10,000.

Preferred is where M is $R_3SiO_{0.5}$ wherein R is methyl (*e.g.* trimethylsiloxy), D is $R_2SiO_{1.0}$ wherein R is methyl (*e.g.* dimethylsiloxy); and b is 1-50,000; and c and d are 0; wherein the compound is dimethicone. Preferably the dimethicone is a liquid at room temperature and has a viscosity ranging from about 10-100,000 centipoise at 25° C.

Also preferred is where M is trimethylsiloxy, D is dimethylsiloxy, b is 1-50,000, as above, and wherein D' is $RR^4SiO_{1.0}$ wherein R is methyl and R^4 is a C_{7-30} , preferably C_{14-20} straight or branched chain alkyl; c is 1-50,000; and d is 0; wherein the compound is a C_{14-20} alkyl dimethicone, in particular, cetyl dimethicone. Preferably, this silicone is a waxy solid or semi-solid at 25° C.

Also preferred is where M is trimethylsiloxy, D is dimethylsiloxy, b is 1-50,000, D' is $RR^4SiO_{1.0}$ wherein R is methyl and R^4 is a C_{7-30} , preferably C_{14-20} straight or branched chain alkyl; and c is 1-50,000; and D'' is $RR^6SiO_{1.0}$ wherein R is methyl and R^6 is $(CH_2)_o-O-PE$ wherein o is 0-40 and PE is $(C_2H_4O)_x(C_3H_6O)_yH$ and wherein x is 1-10,000 and y is 0-10,000. A particularly preferred compound having this general formula is cetyl dimethicone copolyol, tradename ABIL WE 09 or ABIL WS 08. The cetyl dimethicone copolyol may be used alone or in conjunction with other non-silicone organic emulsifiers and oils. Preferred is where the cetyl dimethicone copolyol is in an admixture with other non-silicone organic emulsifiers and oils. In particular, blends of 25-50% of the organosiloxane emulsifier, 25-50% of a non-silicone organic emulsifier, and 25-50% by weight monoester oils are preferred. For example, the mixtures identified by the C.T.F.A. names cetyl dimethicone copolyol (and) polyglyceryl 4-isostearate (and) hexyl laurate, or

cetyl dimethicone copolyol (and) polyglyceryl-3 oleate (and) hexyl laurate both work well. These blends contain approximately 25-50% of each ingredient, for example ABIL WE 09 contains approximately, by weight of the total ABIL composition, 25-50% cetyl dimethicone copolyol, 25-50%, polyglyceryl 4-isostearate, and 25-50% of hexyl laurate
 5 which is a monoester oil.

C. M_eT_f

The composition of the invention may comprise at least one silicone having the general formula M_eT_f wherein M has the empirical formula as defined above with respect to
 10 the $MD_bD'_cD''_dM$ silicone and T is a trifunctional siloxy unit having the empirical formula $RSiO_{1.5}$ or $R^8SiO_{1.5}$, wherein R is methyl and R^8 is a C_{2-40} straight or branched chain alkyl which may be substituted with one or more hydroxyl or halogen radicals. Typically, preferred M_eT_f silicones are made by formed by the hydrolysis and condensation of methyltrimethoxy silane according to procedures well known in the art. Preferably the M_eT_f
 15 silicone is a solid at room temperature, and is more preferably in the particulate form having particle size of about 0.05 to 50 microns. In the preferred embodiment of the invention the composition comprises 0.1-15%, preferably 0.5-12%, more preferably 1-8% by weight of the total composition of the M_eT_f silicone. One type of M_eT_f silicone that may be used in the invention has the general formula M_3T and is referred to as 1,1,1,3,5,5,5-heptamethyl-3-
 20 trimethylsiloxy-trisiloxane. Preferred are M_eT_f silicones wherein M is $R_3SiO_{0.5}$ and T is $RSiO_{1.5}$ wherein R is methyl, and e and f are each 1-1,000, preferably 1-500. Particularly preferred is a M_eT_f silicone which is polymethylsilsesquioxane. This silicone may be purchased from Kobo Products Inc., under the tradename Tospearl 145A. The silicone is a fine white powder having a particle size of 3.5 to 6.0 microns.

25

D. M_gQ_h

The composition of the invention may comprise at least one silicone having the general formula M_gQ_h wherein M, g, and h are as defined above, and Q is a quadrifunctional siloxy unit having the empirical formula SiO_2 or $SiO_{4/2}$. Suitable M_gQ_h silicones are
 30 disclosed in U.S. Patent No.s 4,725,658 and 5,334,737, which are hereby incorporated by reference. These particular silicones are silicone esters which may be liquid or solid at 25° C., and have the general formula M_2Q . The preferred M_gQ_h silicones are made by hydrolysis and condensation of trimethoxysilane and/or trimethylchlorosilane according to procedures well known in the art, thus they will contain very small amounts of silanol
 35 and/or alkoxy endgroups. Such silicones, also referred to as MQ resins, and their manufacture, are set forth in U.S. Patent No.s 2,676,182; 3,541,205, and 3,836,437, all of

- which are hereby incorporated by reference in their entirety. The M_gQ_h silicones used in the compositions of the invention generally satisfy the relationship: $R_nSiO(4-n)/2$ wherein n is a value between 1.0 and 1.50 and R is methyl. Preferably, the M_gQ_h resin is trimethylsiloxy silicate and the ratio of M to Q units is 0.5 to 1 to 1.5 to 1 respectively and is in the form of
- 5 a solid particulate having a particle size ranging from about 0.05 to 50 microns. Trimethylsiloxy silicate is available from Dow Corning Corporation under the tradename Dow Corning 749 fluid, which is a fluid containing about 50% trimethylsiloxy silicate and about 50% cyclomethicone. The fluid has a viscosity of about 200 to 700 centipoise at 25° C., and a specific gravity of 1.00 to 1.10 at 25° C., and a refractive index of 1.40 to 1.41.
- 10 Preferably, the compositions of the invention comprise about 1-45%, preferably 2-40%, more preferably 5-30% by weight of the total composition of the M_gQ_h silicone.

III. OTHER INGREDIENTS

- The compositions of the invention may additionally comprise other ingredients
- 15 which enhance the performance of the composition, such as particulate matter, synthetic polymers, waxes, sunscreens, preservatives, antioxidants, and so on.

A. Particulate Matter

- The composition of the invention may contain 1-50%, preferably 7-45%, more
- 20 preferably 10-40%, by weight of the total composition, of pigments and/or powders, referred to as particulate matter, having a particle size of 0.02 to 100, preferably 0.5 to 100, microns. The particulate matter may be colored or non-colored (for example white). Suitable particulates include bismuth oxychloride, titanated mica, fumed silica, spherical silica, polymethylmethacrylate, polyethylene, polypropylene, micronized teflon, boron
- 25 nitride, acrylate copolymers, aluminum silicate, aluminum starch octenylsuccinate, bentonite, calcium silicate, cellulose, chalk, corn starch, diatomaceous earth, fuller's earth, glyceryl starch, hectorite, hydrated silica, kaolin, magnesium aluminum silicate, magnesium trisilicate, maltodextrin, montmorillonite, microcrystalline cellulose, rice starch, silica, talc, mica, titanium dioxide, zinc laurate, zinc myristate, zinc rosinate, alumina, attapulgite,
- 30 calcium carbonate, calcium silicate, dextran, kaolin, nylon, silica silylate, silk powder, sericite, soy flour, tin oxide, titanium hydroxide, trimagnesium phosphate, walnut shell powder, or mixtures thereof. The above mentioned powders may be surface treated with lecithin, amino acids, mineral oil, silicone oil or various other agents either alone or in combination, which coat the powder surface and render the particles more lipophilic in
- 35 nature.

The particulates may also include various organic and inorganic pigments. The organic pigments are generally various aromatic types including azo, indigoid, triphenylmethane, anthraquinone, and xanthine dyes which are designated as D&C and FD&C blues, browns, greens, oranges, reds, yellows, etc. Organic pigments generally consist of insoluble metallic salts of certified color additives, referred to as the Lakes, in particular the Lakes of D&C and FD&C colors. Inorganic pigments include iron oxides, ultramarines, chromium, chromium hydroxide colors, and mixtures thereof.

Preferably the composition will contain both pigmented and non-pigmented particulates. Obviously the percentage of pigments used in the particulate phase will depend on the type of cosmetic being formulated. Color cosmetics generally have a much higher concentration of color than other types of cosmetics. Generally the weight ratio of pigmented to non-pigmented particulates range from 1:50 to 50:1. It should be noted that particulates that are white or have no color are considered non-pigmented particulates in accordance with the invention, while particulates which exhibit color other than white are considered pigmented particulates in accordance with the invention.

B. Wax

Preferably, the composition comprises about 0.1-70%, preferably 1-30%, more preferably 1-25% by weight of a cosmetically acceptable natural or synthetic wax. The waxes that can be used are solid or semi-solid waxes having a melting point of 30 to 120° C. and generally includes animal waxes, plant waxes, mineral waxes, silicone waxes, synthetic waxes, and petroleum waxes.

Examples of waxes in accordance with the invention include bayberry, beeswax, candelilla, carnauba, ceresin, cetyl esters, hydrogenated jojoba oil, hydrogenated jojoba wax, hydrogenated microcrystalline wax, hydrogenated rice bran wax, japan wax, jojoba butter, jojoba esters, jojoba wax, lanolin wax, microcrystalline wax, mink wax, montan acid wax, montan wax, ouricury wax, ozokerite, paraffin, PEG-6 beeswax, PEG-8 beeswax, rice bran wax, shellac wax, spent grain wax, sulfurized jojoba oil, synthetic beeswax, synthetic candelilla wax, synthetic carnauba wax, synthetic japan wax, synthetic jojoba oil, synthetic wax, stearoxy dimethicone, dimethicone behenate, stearyl dimethicone, and the like, as well as synthetic homo- and copolymer waxes from the ethylene series. In the preferred embodiment of the invention the waxes are either alone or in combination with a petroleum wax such as shellac, and a plant wax such as ozokerite.

C. Synthetic Polymers

The compositions of the invention preferably comprise one or more synthetic polymers. Suggested ranges are 0.1-30%, preferably 0.5-25%, more preferably 1-20% by weight of the total composition. The synthetic polymer will cause the composition to give an improved film on the skin or lips, and may also cause improved transfer resistance and/or plasticity of the film and improved adhesion of the film to skin and lips. The synthetic polymer may be a liquid or solid at 25° C., but is preferably a liquid. A variety of synthetic polymers are suitable, including homo- or copolymers of monomers such as acrylic acid, methacrylic acid or C₁₋₃₀ esters of acrylic or methacrylic acid, vinyl pyrrolidone, saturated methylene diphenyl diisocyanate, C₁₋₃₀ hydroxy esters of acrylic or methacrylic acid, vinyl acetate, vinyl isodecanoate, styrene, and olefins such as ethylene, propylene, butene, pentene, decene, hexadecene, and so on. The synthetic polymers may be copolymers of the monomer units mentioned above, or may be copolymerized with various organic compounds such as polyalkylene glycols, paraffinic hydrocarbons, alkoxylated alcohols and the like. Preferred are copolymers of monomers such as vinyl pyrrolidone, saturated methylene diphenyl diisocyanate, acrylic acid or methacrylic acid and C₁₋₃₀ esters thereof, or olefins; and organic compounds such as alkoxylated alcohols, or polyalkylene glycols. Examples of suitable alkoxylated alcohols include beheneth, steareth, ceteth, laureth, and so on, where the number of repeating ethylene oxide units ranges from 2 to 200. Examples of suitable alkylene glycols include ethylene glycol, propylene glycol, butylene glycol and so on. One preferred synthetic polymer is the copolymer of vinylpyrrolidone and an olefin, hexadecene, known as PVP/hexadecene copolymer, which is sold by International Specialty Products under the tradename Ganex. Another preferred synthetic polymer is a copolymer of saturated methylene diphenyl diisocyanate and a polyalkylene glycol, in particular, polypropylenel glycol, which is known as PPG-51 SMDI copolymer. This copolymer is available from Penederm under the tradename Polyolprepolymer-14.

D. Sunscreens

Preferably, the composition contains one or more sunscreens in a range of about 0.01-10%, preferably 0.05-8%, more preferably 0.1-5% by weight of the total composition. A sunscreen is defined as an ingredient that absorbs at least 85 percent of the light in the UV range at wavelengths from 290 to 320 nanometers, but transmit UV light at wavelengths longer than 320 nanometers. Sunscreens generally work in one of two ways. Particulate materials, such as zinc oxide or titanium dioxide, as mentioned above, physically block ultraviolet radiation. Chemical sunscreens, on the other hand, operate by chemically reacting upon exposure to UV radiation. Suitable sunscreens that may be included in the compositions of the invention are set forth on page 582 of the CTFA Cosmetic Ingredient

Handbook, Second Edition, 1992, as well as U.S. Patent No. 5,620,965, both of which are hereby incorporated by reference. Examples of such sunscreen materials are p-aminobenzoic acid (PABA), cinoxate, diethanolamine p-methoxycinnamate (DEA-methoxycinnamate), Digalloyl trioleate, dioxybenzone (Benzophenone-8), ethyl 4-[bis-(hydroxypropyl)] aminobenzoate (ethyl dihydroxypropyl PABA), 2-ethylhexyl-2-cyano-3,3-diphenylacrylate (octocrylene), ethylhexyl p-methoxycinnamate (Octyl methoxycinnamate), 2-ethylhexyl salicylate (Octyl salicylate), glyceryl aminobenzoate (Glyceryl PABA), homosalate, lawsone with dihydroxyacetone, menthyl anthranilate, oxybenzone (Benzophenone-3), Padimate A (Pentyl Dimethyl PABA), Padimate O, (Octyl Dimethyl PABA), 2-Phenylbenzimidazole-5-sulfonic acid (Phenylbenzimidazole Sulfonic acid), Red Petrolatum, Sulisobenzene (Benzophenone-4), triethanolamine salicylate (TEA-Salicylates), and so on.

E. Preservatives

15 Preferably the composition comprises one or more preservatives in ranges of about 0.001-10%, preferably 0.005-8%, more preferably 0.01-5% by weight of the total composition. Examples of suitable preservatives are parabens, such as methyl, ethyl, and propyl parabens, and the like.

F. Antioxidants and/or Vitamins

20 The compositions of the invention may contain vitamins and/or coenzymes, as well as antioxidants. If so, 0.001-10%, preferably 0.01-8%, more preferably 0.05-5% by weight of the total composition are suggested. Suitable vitamins include ascorbic acid and derivatives thereof, the B vitamins such as thiamine, riboflavin, pyridoxin, and so on, as
25 well as coenzymes such as thiamine pyrophosphate, flavin adenin dinucleotide, folic acid, pyridoxal phosphate, tetrahydrofolic acid, and so on. Also Vitamin A and derivatives thereof are suitable. Examples are Vitamin A palmitate, acetate, or other esters thereof, as well as Vitamin A in the form of beta carotene. Also suitable is Vitamin E and derivatives thereof such as Vitamin E acetate, nicotinate, or other esters thereof. In addition, Vitamins
30 D and K are suitable.

Suitable antioxidants are ingredients which assist in preventing or retarding spoilage. Examples of antioxidants suitable for use in the compositions of the invention are potassium sulfite, sodium bisulfite, sodium erythrobate, sodium metabisulfite, sodium sulfite, propyl gallate, cysteine hydrochloride, butylated hydroxytoluene, butylated
35 hydroxyanisole, and so on.

G. Biological Additives

The composition may comprise one or more biological additives. Suggested ranges are about 0.001-8%, preferably 0.01-6%, more preferably 0.05-5% by weight of the total composition. Suitable biological additives include extracts of plant or animal matter,

- 5 preferably plant matter. Examples of desirable biological additives include extracts of aloe, camilla, acacia, blackberry, blueberry, carrot, and so on.

The compositions may also contain a variety of other ingredients such as humectants, water, emollients, and so on.

- 10 The invention will be further described in connection with the following examples, which are set forth for the purposes of illustration only.

EXAMPLE 1

A liquid lipstick was made according to the following formula:

		w/w%
15	1 Shellac wax	1.000 (wax)
	1 Synthetic wax	0.750 (wax)
	1 PVP/hexadecene copolymer	2.000 (synthetic polymer)
	1 Neopentyl glycol dioctanoate	5.600 (diester)
	1 Trioctyl dodecyl citrate	3.000 (triester)
	1 Cetyl dimethicone	10.000 (MD _b D' _c D'' _d M - liquid)
	1 Stearyl dimethicone	1.500 (MD _b D' _c D'' _d M - waxy solid)
20	1 PPG-51/SMDI Copolymer	7.000 (synthetic polymer)
	1 Octyl methoxycinnamate	2.200 (sunscreen)
	1 Methyl paraben	0.300 (preservative)
	1 Propyl paraben	0.100 (preservative)
	1 Butylated hydroxy anisole	0.200 (antioxidant)
	1 Sorbic acid	0.200 (antioxidant)
	5 Cyclomethicone/trimethylsiloxysilicate (50:50)	34.68 (D _a liquid + M _c Q _b solid)
25	1 Cetyl dimethicone copolyol/polyglyceryl-4-isostearate/hexyl laurate (33:34:33)	3.350 (MD _b D' _c D'' _d M liquid + nonionic surfactant + monoester)
		(surfactant + monoester)
	3 D&C Red #7 Calcium Lake	0.180 (pigment)
	3 FD&C Yellow #5 Aluminum Lake	0.120 (pigment)
	3 Red iron oxide	0.420 (pigment)
	3 Black iron oxide	0.180 (pigment)
30	2 Dimethicone	4.800 (MD _b D' _c D'' _d M - liquid)
	2 Acrylates copolymer	1.200 (powder)
	4 Titanium dioxide, mica, iron oxides	3.500 (pigment + powder)
	4 Bismuth oxychloride	3.500 (powder)
	4 Polymethylsilsesquioxane	3.000 (M _c T _e)
	4 Mica	11.320 (powder)

- 35 Separately, the Sequence 2 ingredients were roller milled together. Separately, the Sequence 3 ingredients were roller milled in a portion of the Sequence 5 ingredients. The

Sequence 1 ingredients were combined and heated to 95° C. with mixing until the ingredients were mixed. The Sequence 2 and Sequence 3 premixes were added to the Sequence 1 mixture. The batch was covered for the remainder of the procedure. The temperature of the mixture was reduced to 85° C. The Sequence 4 ingredients were then
 5 added, followed by the Sequence 5 ingredients. The temperature was further reduced to 80° C. The composition was poured into vials and allowed to cool to room temperature.

EXAMPLE 2

10 A lipstick in the stick form was made according to the following formula:

	w/w%
1 Synthetic wax	4.00 (wax)
1 Ozokerite	0.80 (wax)
1 Shellac wax	1.50 (wax)
1 Diisostearyl malate	8.00 (diester)
1 Cetyl dimethicone	12.00 (MD _b D' _c D'' _d M)
15 1 PPG-51/SMDI copolymer	6.00 (synthetic polymer)
1 Octyl methoxycinnamate	2.20 (sunscreen)
1 Propyl paraben	0.10 (preservative)
1 Butylated hydroxy anisole	0.10 (antioxidant)
1 Stearyl dimethicone	1.55 (MD _b D' _c D'' _d M)
1 Vitamin E acetate	2.00 (vitamin)
1 Aloe extract	1.00 (biological additive)
20 2 Pigments	10.45 (pigment)
3 Titanium dioxide/mica	5.00 (powder)
3 Bismuthoxychloride	2.00 (powder)
3 Polymethylsilsesquioxane	4.00 (M _c T _p)
3 Mica	5.10 (powder)
5 Lanolin oil	1.00 (oil)
5 Dimethicone	3.00 (MD _b D' _c D'' _d M)
6 Cyclomethicone/trimethylsiloxysilicate (50:50)	25.20 (MD _b D' _c D'' _d M + M _g Q _h)
25 4 Isododecane	5.00 (hydrocarbon)

The Sequence 2 ingredients were roller milled into a portion of the Sequence 6 ingredients. The mixture was combined with the Sequence 1 ingredients and heated with mixing to a temperature of 95° C. until uniform. The remaining Sequence 2 ingredients
 30 were added to the mixture. The batch was covered for the remainder of the procedure. The heat was reduced to 85° C. The Sequence 3 and Sequence 4 ingredients were added and mixed well. The Sequence 5 ingredients were combined and added to the mixture, followed by the Sequence 6 ingredients. The mixture was poured into lipstick molds when the temperature reached 85° C. and allowed to cool to form sticks.

35

WE CLAIM:

1. A pigmented cosmetic composition comprising at least one silicone compatible organic oil and at least two silicones selected from the group consisting of:

- (A) D_a
- 5 (B) $MD_bD'_cD''_dM$
- (C) M_eT_f
- (D) M_gQ_h

wherein a is 3-6

- b is 1-1,000,000, preferably 1-50,000, more preferably 1-5,000
- 10 c is 0-1,000,000, preferably 0-50,000, more preferably 0-5,000
- d is 0-1,000,000, preferably 0-50,000, more preferably 0-5,000
- e is 1-1,000
- f is 1-1,000
- g is 1-1,000; and
- 15 h is 1-1,000.

2. The composition of claim 1 wherein the silicone compatible organic oil is selected from the group consisting of:

- (a) a mono-, di-, or triester,
- (b) a hydrocarbon oil,
- 20 (c) lanolin oil; and
- (d) mixtures thereof.

3. The composition of claim 2 wherein the monoester is the reaction product of a C_{6-22} fatty acid and a C_{2-30} aliphatic alcohol.

4. The composition of claim 3 wherein the monoester is the reaction product of a 25 C_{2-8} alcohol and a C_{14-22} fatty acid.

5. The composition of claim 4 wherein the monoester is the reaction product of hexyl alcohol and lauric acid.

6. The composition of claim 2 wherein the diester is formed by the reaction of a fatty alcohol and a dicarboxylic acid.

30 7. The composition of claim 6 wherein the fatty alcohol has 14 to 22 carbon atoms, and the dicarboxylic acid is an alpha hydroxy acid.


8. The composition of claim 7 wherein the fatty alcohol is isostearyl alcohol and the alpha hydroxy acid is malic acid.

9. The composition of claim 2 wherein the triester is the reaction product of a 35 tricarboxylic acid and an aliphatic or aromatic alcohol.

10. The composition of claim 9 wherein the tricarboxylic acid is an alpha hydroxy acid and the aliphatic alcohol has 14 to 22 carbon atoms.

11. The composition of claim 1 wherein the D_a silicone is a cyclic silicone having the formula:

5



10

wherein $n = 3-6$.

12. The composition of claim 1 wherein the $MD_bD_c'D_d''M$ silicone M is
15 trimethylsiloxo; D is dimethylsiloxo; b is 1-50,000; and c and d are 0; the compound being dimethicone.

13. The composition of claim 12 wherein the dimethicone is liquid and has a viscosity of 10 to 100,000 centipoise at 25°C.

14. The composition of claim 1 wherein the $MD_bD_c'D_d''M$ silicone M is
20 trimethylsiloxo; D is dimethylsiloxo; b is 1-50,000; D' is $RR^4SiO_{1.0}$ wherein R is methyl and R^4 is a C_{14-20} straight or branched chain alkyl; c is 1-50,000; and d is 0.

15. The composition of claim 14 wherein R^4 is C_{16} and the silicone is cetyl dimethicone.

16. The composition of claim 1 wherein the $MD_bD_c'D_d''M$ silicone M is
25 trimethylsiloxo; D is dimethylsiloxo; b is 1-50,000; D' is $RR^4SiO_{1.0}$ wherein R is methyl and R^4 is a C_{14-20} straight or branched chain alkyl; c is 1-50,000; D' is $RR^6SiO_{1.0}$ wherein R is methyl and R^6 is $(CH_2)_o-O-PE$ wherein o is 0-40 and PE is $(C_2H_4O)_x(C_3H_6O)_yH$ and wherein x is 1-10,000 and y is 0-10,000.

17. The composition of claim 16 wherein the silicone is cetyl dimethicone copolyol.
30 18. The composition of claim 1 further comprising 1-50% by weight of the total composition of particulate matter.

19. The composition of claim 1 further comprising 0.1-30% by weight of the total composition of one or more synthetic polymers.

20. The composition of claim 1 further comprising 0.1-70% by weight of the total
35 composition of one or more waxes.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/11359

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : A61K6/00; A61K 7/00

US CL : 424/401

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 424/64, 400, 401

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EAST

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5,496,544 A (MELLUL et al) 05 March 1996, see entire document, especially, abstract; column 2, lines 47-62.	1-20

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Z* document member of the same patent family
C document referring to an oral disclosure, use, exhibition or other means	
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

23 JUNE 2000

Date of mailing of the international search report

13 JUL 2000

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

D. Jones

Telephone No. (703) 308-1235